

**Property cards**

<b>Melting point /°C</b> 3730 sublimes <b>Boiling point /°C</b> - <b>Electrical conductor</b> No <b>Hardness</b> Extremely hard <b>Density /g cm<sup>-3</sup></b> 3.51	<b>Melting point /°C</b> -95 <b>Boiling point /°C</b> 54 <b>Electrical conductor</b> No <b>Hardness</b> Soft and brittle <b>Density /g cm<sup>-3</sup></b> 0.79
<b>Melting point /°C</b> 114 sublimes <b>Boiling point /°C</b> 184 <b>Electrical conductor</b> No <b>Hardness</b> Soft and brittle <b>Density /g cm<sup>-3</sup></b> 4.93	<b>Melting point /°C</b> 801 <b>Boiling point /°C</b> 1697 <b>Electrical conductor</b> Solid no Molten yes <b>Hardness</b> Medium and brittle <b>Density /g cm<sup>-3</sup></b> 2.17
<b>Melting point /°C</b> 1530 <b>Boiling point /°C</b> 3000 <b>Electrical conductor</b> Yes <b>Hardness</b> Very hard <b>Density /g cm<sup>-3</sup></b> 7.86	<b>Melting point /°C</b> 1610 <b>Boiling point /°C</b> 2230 <b>Electrical conductor</b> No <b>Hardness</b> Very hard <b>Density /g cm<sup>-3</sup></b> 2.5
<b>Melting point /°C</b> 0 <b>Boiling point /°C</b> 100 <b>Electrical conductor</b> No <b>Hardness</b> Soft and brittle <b>Density /g cm<sup>-3</sup></b> 1	<b>Melting point /°C</b> 5 <b>Boiling point /°C</b> 80 <b>Electrical conductor</b> No <b>Hardness</b> Soft and brittle <b>Density /g cm<sup>-3</sup></b> 0.88
<b>Melting point /°C</b> Low, melts over a range <b>Boiling point /°C</b> - <b>Electrical conductor</b> No <b>Hardness</b> Soft <b>Density /g cm<sup>-3</sup></b> 0.92 to 0.96	<b>Melting point /°C</b> -272 <b>Boiling point /°C</b> -162 <b>Electrical conductor</b> No <b>Hardness</b> Soft and brittle <b>Density /g cm<sup>-3</sup></b> 0.424